

WO01/64385

3/pst

PCT/EP01/01932

METHOD FOR MANUFACTURING A SURFACE-ALLOYED CYLINDRICAL,
PARTLY CYLINDRICAL OR HOLLOW CYLINDRICAL STRUCTURAL
MEMBER AND DEVICE FOR IMPLEMENTING THE METHOD

DESCRIPTION

The invention relates to a method for manufacturing a surface-alloyed cylindrical, partly cylindrical or hollow cylindrical structural member where an energy beam having a linear radiation area, hereinafter called a linear focus, is directed onto a workpiece surface whereby the workpiece surface is melted and a hard-material or alloy powder is fed into the molten surface, and a device for implementing the method.

WO 97/10067 discloses a method for coating metal workpieces in which metal-containing powder is melted using a laser beam and deposited into the surface of the metal workpiece. According to Claim 1 of the WO document, the powder should be fed into the melting region coaxially to the laser beam and distributed over a fairly large area in the form of 0.1 to 1 mm wide tracks.

In order to implement the disclosed method according to a preferred example of embodiment of WO 97/10067 there is a device for supplying powder coaxially to a laser beam focussing head which can be moved relative to one other along three axes. However the moveability is limited only because of the necessary control technology.

For a coating plant which is to be used industrially track widths of 0.1 to 1 mm are uneconomical and devices moveable along three axes are too expensive. In addition, larger areas such as, for example, the inner bearing

surfaces of cylinder walls, cannot be coated directly using the known device.

Bearing surface treatment installations are known for applying a coating to inner bearing surfaces, consisting of a rotatable clamping device for a cylinder block, a laser treatment unit with a beam head which is connected to a powder supply device, and a transfer unit which positions the cylinder block in front of the laser treatment unit, and a drive for moving the transfer unit along a transfer axis.

For these bearing surface treatment installations high requirements are imposed on the precision regarding the alignment of the installation parts and their wear behaviour since the engine blocks manufactured using these are later fitted with separately manufactured pistons and for cost reasons expensive after-treatment should be avoided if possible.

The object of the present invention is to develop an economical surface treatment method for cylindrical or partly cylindrical surface shapes, which can be used industrially, with which a tribologically optimised heat-treatable hollow cylindrical blank can be favourably manufactured. The new device for implementing the method should operate with a high accuracy and should make it possible to achieve good adjustability for the various process parameters.

This object is solved according to the invention by the features specified in the Claims. In numerous tests it was established that a high accuracy and lower wear behaviour of the bearing surface treatment installation and the parts produced thereon can be achieved if

WO01/64385

- 4 -

PCT/EP01/01932

- a) Linear focus with line widths greater than 4 mm transverse to the feed direction,
- b) High-energy beam having a wavelength between 780 and 940 nm and a
- c) Powder feed can be produced in the downhand position associated with a specific energy input of 5,000 - 600,000 W/cm².
- d) The cooling rate of 200 - 600 K/s

helps to achieve controlled Si grain distribution and the formation of silicon primary crystals with phase diameters of up to 80 µm in the eutectically solidifying residual melt.

The process step e) means that the hard material, e.g. the silicon must be completely dissolved in the melting bath.

The duration depends on the specific laser power. If the linear focus acts for too long, pore formation occurs as a result of evaporation of the aluminium or the matrix alloy and the hard materials can clump together.

The feed rate should be less than 10,000 mm/min according to process step f) otherwise the input energy is not sufficient for entry of the hard material into the melt. At the given power the laser beam should be coupled into the matrix with an energy yield of 40 - 60 %. If the cooling rate is too high > 600 K/sec, the solution time is not sufficient for the hard material whereas below 200 K/sec cracks appear in the alloying zone since too much hard material goes into solution.

WO01/64385

- 5 -

PCT/EP01/01932

In a preferred embodiment of the invention several energy beam units can be used as further parameters to control the structural properties by spatially variable cooling rates.

By this means it is possible to set spatially different surface hardnesses which allow purely mechanical further treatment and final treatment. If the surface hardness is greater than 160 HV, honing can be carried out using diamond without scoring and without smearing. Then in a further treatment process the silicon primary crystals or other hard materials of $> 1 \mu\text{m}$ diameter can be exposed purely mechanically on the surface by removing $< 1 \mu\text{m}$.

According to a preferred example of embodiment, the linear focus should be directed onto the surface to be alloyed in a double track one after the other (relative to the feed direction) so that a partial heat treatment can be achieved by hardening, recrystallisation, lengthening the precipitation time, homogenisation and phase coarsening of the precipitates.

According to another preferred case of application the powder components can also be applied in a double track so that different compositions and rates of application are possible here, e.g. the build-up of gradient materials with controlled alloy formation.

A controllable aperture which serves to lengthen or shorten the linear focal width seen in the feed direction can be used in a preferred fashion to start up and switch off the coating device.

Unlike the known coating device according to DE 198 17 091 A1 (NU TECH/VAW motor GmbH) , an energy beam device

moveable along one axis and a structural member moveable along multiple axes is used here. Of particular advantage here is that the rotation speed of the workpiece is variable in order to achieve a coarse-phase structure (by slow rotation) or a fine-celled or fine-phase structure (by faster rotation) at the same energy input.

As has already been mentioned, a double track can be used to alloy various types of alloy. The powder can be applied to the surface of the workpiece in a single stage (a single powder beam) or in several stages (several powder beams) via suitably shaped powder slit nozzles. The linear focal width is at least 4 mm, preferably 5 to 15 mm.

A particular feature of the method according to the invention is that variable penetration depths between 100 - 2500 μm can be achieved by varying the feed rate and/or by surface-related energy input. A diode laser with the wavelength range specified in the Claim is preferably used for improved coupling which, in conjunction with a previously applied hard-material powder and hard-material-containing powder, especially Si or Si-containing powder, can achieve excellent heat input deep inside the structural member.

The invention is explained in greater detail subsequently with reference to several examples of embodiment. The drawings are as follows:

Figure 1 Cross-section through a bearing surface treatment installation according the invention during the treatment of a cylinder block,

WO01/64385

- 7 -

PCT/EP01/01932

Figure 2 Longitudinal section through a bearing surface treatment installation according the invention during insertion into a four-cylinder in-line engine block,

Figures 3 - 5 Enlarged views of section X in Figure 2,

Figure 6 Cross-section as in Figure 1 with two beam heads,

Figure 7 Schematic diagram to explain the method of manufacture according to the invention,

Figure 8 Longitudinal section through a bearing surface treatment installation according the invention with powder supplied via a vibrating conveyer chute,

Figure 9 Cross-section along AA in Figure 8,

Figure 10 Enlarged section Y from Figure 8,

Figure 11 Principle of a screw conveyer similar to Figure 1.

Figure 1 shows a cylinder block 2 of a four-cylinder in-line engine clamped in a clamping device 1 such that the longitudinal axis of the in-series engine is in the direction of the gravity vector.

A laser treatment unit 3 projects with the beam head 4 into the bore of the cylinder block 2. The beam head can be moved in the direction of a transfer axis 10 (perpendicular to the plane of the drawing).

From the beam head 4 a laser beam emerges in the direction of gravity, which impacts on the surfaces of

the cylinder wall in the beam incidence zone 12 and there forms a heating zone 11, a melting zone 12 and a solidification zone 13.

A powder supply device 5 also opens out in the vicinity of the beam incidence zone, applying a powder jet 9 either directly in the beam direction or, seen in the feed direction, shortly before the point of incidence of the laser beams onto the cylinder wall to be treated. The application of the powder can be used to influence the structural properties both from the alloy point of view and also from the type of structure formation. This is achieved, for example, by the type and quantity of powder supplied.

In a variant not shown several powder supply devices can be inserted simultaneously in the cylinder bore. The laser treatment can also be accomplished using several beam heads at the same time.

Figure 2 shows a bearing surface treatment installation constructed according to the invention in a four-cylinder in-line engine. The cylinder block 2 can be seen in the longitudinal section, i.e. perpendicular to the plane of the drawing in Figure 1. The clamping device 1 is located on a clamping table 1a and a turntable 1b which is connected to a drive 6 to move the transfer unit along a transfer axis 10.

The direction of the arrow 6a indicates the direction in which the engine block 2 is turned during treatment. Here it is important that the powder supply device 5 is positioned in front of the laser head 4, as shown in Figure 2, section X.

Figure 7 is a schematic showing the method according to the invention for manufacturing a surface-alloyed cylindrical or partly cylindrical structural member. It

WO01/64385

- 10 -

PCT/EP01/01932

involves first directing an energy beam having a linear beam area (also called a linear focus) onto a workpiece surface. The workpiece surface is thereby melted and a hard material or alloy powder is fed into the molten surface.

As shown in Figure 7, in the zone of incidence of the energy beam there forms a locally bounded melting bath with a heating and melting front 20, a solution zone or remelting zone 21 and a solidification front 22.

At the side of the energy beam 23 a quantity of powder 24 is applied to the surface of the structural member 26 in the direction of gravity. The quantity of powder 24 is co-ordinated with the feed movement 27 of the workpiece or structural member 26, where the width of the powder jet transverse to the plane of the drawing in Figure 7 approximately corresponds to the width of the energy beam 23 (also measured transverse to the plane of the drawing).

It can be seen from Figure 7 how the powder supplied to the workpiece surface is heated in the solidification front and then dissolved at the latest in the energy beam 23 in the melting bath. Tests have shown that at a wavelength of 780 to 940 nm the coupling of the energy beam into the metal matrix is optimised but also the powder undergoes optimised rapid heating and is dissolved in the melt in contact with the liquefied matrix alloy.

As shown by the arrows 28 in Figure 7, convection takes place in the solution zone so that the homogenisation process is accelerated in the melting zone. This is made possible by the energy beam having a specific power of at least 10^4 W/cm². It can be seen from polished sections

WO01/64385

- 11 -

PCT/EP01/01932

that the hard material or alloy powder is only uniformly distributed in the melting bath if the linear focus has acted on the solution zone for a sufficiently long time. The precise values can be determined experimentally.

The powder material dissolved uniformly in the melt is then subjected in the solidification zone 22 to directional solidification at a cooling rate of 200 to 600 K/sec in the solidification front where the feed rate is between 500 and 10,000 mm/min. In a variant of the method according to the invention the powder is transferred to the surface of the structural member in the gas stream so that a certain quantity of powder can already penetrate into the melting zone as a result of the kinetic energy.

Further tests have shown that the energy beam is preferably split before the zone of incidence where a first part beam is deflected into the heating and melting zone and a second part beam is deflected behind the solidification front for thermal structural treatment. The formation of the structure can be specifically controlled by this method. A device for implementing the method is shown in Figure 6.

Further control of the structure can be achieved by directing the energy beam in the solidification front at a specific power of $< 1 \text{ kW/mm}^2$ onto the surface of the workpiece. It has been found that the time of action of the energy beam in the melting bath for dissolving and homogeneously distributing the hard material or intermetallic phases lies between 0.01 and 1 second.

Said requirements are met by a $\geq 3 \text{ kW}$ diode laser having an adjustable linear focal width. By this means before

The energy beam is deflected and focussed via a diode laser 43 and a laser optical system 44. The vibrating conveyor chute 30 and diode laser 43 are attached to a mounting plate 46 which rests on a feed slide 45. The

If several energy beam units, staggered relative to one another, are directed onto the working surface of the workpiece rotating in the downhand position, the energy beam unit should sweep the working surface rectilinearly.

WO01/64385

- 14 -

PCT/EP01/01932

This produces a flat alloying zone which can be dimensioned according to the delimiting device of the system and/or the rotating movement of the structural member.

Advantageously the energy beam units sweep several lines of the working surface simultaneously. As a result the processing times are shortened and the treated surfaces become more uniform.

An alternative to the powder supply via one or several nozzles shown in Figures 1 to 6 is explained subsequently. This involves supplying powder by means of a screw conveyor or vibrating device which has proved particularly effective at high temperatures and in narrow cylinder bores.

The thermal radiation at high laser powers is very intensive so that normal nozzle materials located in the vicinity of the laser incidence zone cannot withstand the high temperatures or erode. In addition, the powder irradiated above the nozzle is at high pressure and has a strong effect on the gas flow inside the cylinder bore to be processed. The temperature level and the density of the protective gas change with the gas flow so that the efficiency of the laser is subject to severe fluctuations.

With a vibrating conveyor chute 30 these conditions can be controlled significantly better. The temperature level and the protective gas atmosphere are not adversely influenced during the powder supply via a screw conveyor or conveyor chute. High-strength and temperature-resistant materials can be used for the conveyor chute so

For implementation on an industrial scale there was developed a diode laser 43 with a laser optical system 44 which are located in a fixed position relative to the direction of rotation of the structural member inside the rotatable clamping device 32 connected to a drive unit.

The diode laser with the optical system is moved into the cylinder bore 34 by means of a feed slide 45 together with the powder supply device which is located beside the energy beam. It is also possible to deposit the powder on the surfaces facing the beam. This is achieved as in Figure 8 by a conveyor chute 30 with which the powder is loosely sprinkled in the direction of gravity. A pre-deposited powder layer 35 is formed where the outlet height HA of the conveyor chute in Figure 9 is given.

In order to produce spiral or other geometrical guidance for the linear focus the drive unit for the turntable 31 should make it possible to achieve a variable rotation speed. Then the feed slide 45 of the diode laser 43 and the powder supply in the direction of the axis of rotation can be combined with the rotation speed of the engine block 33.

In Figures 10 and 11 the vibrating conveyor chute 30 or screw conveyor 38 produces a powder height HP where the distance from the conveyor device is denoted by HA. The cylinder bore 34 accommodates the laser optical system 44 with the bore diameter 48 and both are moved in a feed slide 45 in the direction of the arrow.

The method described can be used to manufacture surface-alloyed cylindrical or partly cylindrical especially hollow cylindrical structural members. They consist of an aluminium matrix casting alloy and a precipitation zone extending as far as the surface of the structural member comprising an aluminium based alloy with precipitated hard phases. Between the matrix and the precipitation zone there is a eutectic zone supersaturated by primary hard phases (supersaturation zone) where the increase in hardness from the matrix to the surface of the structural

WO01/64385

- 17 -

PCT/EP01/01932

member takes place stepwise. Especially favourable conditions can be achieved if the matrix alloy of the type AlSiCu or AlSiMg is hypoeutectic and in the supersaturated eutectic transition zone there is an alloy of the type AlSi with finely precipitated primary silicon phases smaller than 1 μm , whereas in the precipitation zone there are primary silicon phases of 2 to 20 μm . Then increases in hardness as far as the surface of the structural member of over 200 % can be achieved.